



WOOD FINISHES DIRECT

The following Technical Datasheet is provided by **Bona**

Wood Finishes Direct cannot be held liable for the information contained within this document.

For purchasing information visit:
[Bona Mix and Fill Plus](#)

Bona Mix&Fill Plus

Technical data sheet

Bona Mix&Fill Plus is a high-solids waterborne binder designed for quick and efficient filling of gaps and cavities in wooden floor. The product is mixed with wood dust from the actual floor to be treated which gives a natural colouration that blends in with the rest of the floor. Bona Mix&Fill Plus can be used with most types of wood and for gaps up to 3 mm wide.

- Exceptional filling ability
- Fast drying
- Waterborne yet anti-corrosive (no rust stains)
- Optimized for light to medium coloured timbers
- Very low solvent content

Technical data

Solids content:	~38%
VOC:	max 15 g/lit
Mixing ratio:	10-15% wood dust to 85-90% binder
Drying time, until:	- until subsequent application 15-30 minutes* - until sanding 30-60 minutes* - until finish or oil treatment 1-2 hours*
Application tools:	Stainless steel trowel
Application rate:	~8-12m ² /litre depending on size and quantity of gaps.
Safety	Unclassified
Cleaning:	Wipe tools free from residual material before cleaning with a minimum of water. Dried material can be removed mechanically or by scrubbing with water.
Disposal:	Wastes and emptied containers should be handled in accordance with local regulations.
Storage/transport:	The temperature must not fall below +5°C or exceed +25°C during storage/transport. Reseal the container directly after use.
Shelf life:	1 year from the date of production, in unopened original container.
Pack size:	3x5 litres (44 boxes per pallet)

*Assumes normal, minor gap formation on newly installed floors at 20°C/60% RH room climate. The wider and deeper the gap, the longer the drying time. Gaps wider than 2 mm need drying over night.

Preparations

Ensure floor is acclimatized to its end-use environment, dry and free from wax, dirt and other contamination. Sand the floor to bare wood and to grit 60-80 (before making the final cut). Temperature of the room and the product must not fall below +13°C during application and drying.

Application

1. Shake can thoroughly before use.
2. Mix the product in a container with fine and clean wood dust to a smooth consistency.
3. Apply the mixture across the whole floor using a stainless steel trowel and repeat the procedure if necessary.
4. When the surface is dry, sand off all excess Mix&Fill Plus with a belt and edge sander grit 100-120.

Finishing



Bona[®]

Bona Mix&Fill Plus

Technical data sheet

5. Treat the floor with any Bona coating system according to respective instruction.

Important notes

- Gaps within plank or end-grain floors are normally not filled. Dry filler could partially break loose when shrinkage/expansion occurs.
- Bona takes only responsibility for the delivered product. Due to the wide variety of wood species available and possible applications, no responsibility can be taken for the total installed product. Certain rare wood species (mostly tropical) or chemically treated wood can trigger unforeseen reactions. If in doubt, conduct a test to ensure satisfactory function and colour authenticity.

Finishing



Bona[®]