



WOOD FINISHES DIRECT

The following Product Datasheet is provided by **Morrells**

Wood Finishes Direct cannot be held liable for the information contained within this document.

For purchasing information visit:
[Holzol Decking Oil](#)

Product Data Sheet



holzöl Deck-Oil

Code	Description	Code	Description
7DO/00/30	holzöl Deck-Oil Clear	7DO/02/30	holzöl Deck-Oil Oak
7DO/01/30	holzöl Deck-Oil Teak	7DO/04/30	holzöl Deck-Oil Cedar
7DO/03/30	holzöl Deck-Oil Walnut	7DO/06/30	holzöl Deck-Oil Green
7DO/05/30	holzöl Deck-Oil Larch	Thinners	R047 – White Spirit

Technical Data	holzöl Deck-Oil is formulated on a blend of quality, modified natural oils with a urethane resin for use outside on decking, garden furniture, fences and boats.
Properties	holzöl Deck-Oil is a blend of natural oils modified with urethane resin, suitable for garden furniture, doors, fences, decks, boats etc. Enriched with UV filters, it keeps wood from turning grey, and makes it appear alive and vibrant in tone.
Mixing Guidelines	Supplied ready for use (RFU) but can be thinned up to 15% by volume with the recommended thinner, R047, if required.
Typical Handling	Drying Time: 8 - 12 hours, Recoat Time: 8 - 12 hours Maximum hardness after 24 hours. These times are dependant amounts applied, the absorbency of the wooden substrate and application conditions.
Cleaning	R047 - White Spirit should be used for cleaning equipment.
Coverage	Approximately 10 -12m ² per litre depending upon the application method, absorbency and surface quality of the timber being coated.
System Guidelines	Morrells recommends the following guidance for use of these products : Typical Finish: <ul style="list-style-type: none"> ○ The surfaces of the timber to be coated should be clean, dry and free from oils, greases, waxes, silicones, old finishes etc. ○ Apply an even film of holzöl Deck-Oil by application with a brush, rag or roller over the surface. If required, and especially with exotic timbers, the first coat can be thinned (See Mixing Guidelines). ○ Allow to dry for 8 - 12 hours. ○ Apply a second coat of holzöl Deck-Oil, as above. Allow 24 to completely dry. If required a third coat can be applied. <p>Using these products in systems outside these guidelines can lead to immediate and latent problems with the integrity of the finish.</p>



Morrells Woodfinishes Ltd. Wellington Works, Mill Lane, Woodley, Stockport, Cheshire. SK6 1RN
Tel: 08705 60 61 62 Fax: 08705 604 604 Email: enquiries@morrells.co.uk Web: www.morrells.co.uk

Registered Office: Morrells Woodfinishes Limited. Company no. 785935 VAT. Reg No GB 712 5048 66



Maintenance	The holzöl Deck-Oil should be maintained using a clean, lightly dampened cloth. If the finish becomes “fired” looking or damaged, apply a further coat of holzöl Deck-Oil.
Important Information	<ul style="list-style-type: none"> ➤ Designed for manual (brush, rag or roller) application. ➤ Use only the recommended thinner. Use of non-recommended thinner can cause uneven/patchy drying. ➤ Always test the product on a spare surface or inconspicuous area to assess compatibility, colour and finish. ➤ Colours are only able to be an approximate representation due to the variation in substrate and application methods. ➤ Sawdust, cloths, brushes, papers and similar products containing wet product may cause spontaneous combustion. Either allow to fully dry or drench in water before disposal. ➤ Product should be stored above 5°C and protected from frost. ➤ Optimum application is achieved between 20°C and 25°C with good air movement and ventilation. ➤ Meets the VOC requirements of 2004/42/EC, Annex II(Cat A/i).
Health & Safety	Reference should be made to the appropriate MSDS for these products, which can be found at www.morrells.co.uk The use of appropriate personal protection equipment (PPE) is recommended.

The information provided on this information sheet is based on the best of our knowledge and experience, is given in good faith and should only be regarded as recommendations. No guarantee should be inferred and customers are advised to carry out their own tests under local conditions.

For further technical information contact our Technical Support Team on 0161 406 5300.

