



WOOD FINISHES DIRECT

The following Product Datasheet is provided by **Sadolin**

Wood Finishes Direct cannot be held liable for the information contained within this document.

For purchasing information visit:
[Sadolin Quick Dry Woodstain](#)



Quick Dry Woodstain

Sadolin Quick Dry Woodstain is a multipurpose 6 year woodstain, which colours, enhances and protects exterior wood around the home. It's unique, long lasting and quick drying formulation offers the convenience of being able to complete your job in a day, without compromising on the performance or protection that you have come to expect from traditional woodstains.

Sadolin Quick Dry Woodstain is suitable for windows, doors and conservatories.

Properties	
Composition	Alkyd / Acrylic resin blend dispersed in water. Water based woodstain.
Coating System	2-3 coats of Sadolin Quick Dry Woodstain onto bare or previously stained timber.
Finish	Translucent semi-gloss finish.
Recommended Application Rate	Up to 15m ² per litre on smooth planed timber. This figure is intended as a guide. The actual coverage will depend on a number of factors, including timber species, surface condition, moisture content, method of application and climatic conditions during application.
Minimum Wet Film Thickness	Approximately 80 micrometres @ 13m ² per litre on non-absorbent surfaces. The first coat should be applied liberally in order to satisfy the natural absorption / porosity of the timber surface.
Dry Film Thickness	Approximately 25 micrometres @ 13m ² per litre
Drying Time @ 20°C / 65%RH	Rainproof : Under an hour. Touch Dry : 1 hour. Recoatable : 4-6 hours. Note: Drying times are dependent upon absorption of substrate and drying conditions. Minimum recommended application temperature 8°C. At low temperatures and / or conditions of high relative humidity, drying times will be extended.
Volume Solids	Approximately 30%.
VOC Content	EU limit value for this product (cat. A/ e): 130 g/l (2010). This product contains max 46 g/l VOC
Flash Point	Not applicable.
Colour Range	10 standard colours and 37 tinted shades As with all translucent coatings, the final colour and sheen are dependent on a number of factors, including the timber species, colour and cut, and the presence of any existing coating. A trial application is recommended prior to the commencement of work.
Container Size	Sadolin Quick Dry Woodstain is available in 1 & 2.5 litre containers, dependent on colours.
General Information	The following information is provided for guidance purposes, sample specifications for all Sadolin woodcare finishes are available on the Sadolin website, (www.sadolin.co.uk). All products should be applied in accordance with the manufacturer's instructions, BS 6150: 2006 and BS 8000: Part 1: 1989. Crown Paints are unable to guarantee results as we have no control over the conditions under which products are applied.
Preparation	
General	Timber surfaces must be suitably prepared, clean, sound and dry. The moisture content should not exceed 18% prior to coating. Resinous deposits should be removed. Degrease any exposed bare timber surface by wiping with a cloth dampened with methylated spirits. "Knotting agents" should not be used with Sadolin translucent woodstain systems. Fillers specifically designed for use with timber such as the Sadolin woodfillers should be used for making good any minor surface defects, imperfections and open joints etc. General or All Purpose fillers are not suitable. Only use non - ferrous screws, nails and fixings.
New Timber	Any non preservative treated softwood timber should be treated with two liberal coats of Sadolin Quick Dry Wood Preserver , paying particular attention to end grains, allowing 24 hours drying time between coats and before overcoating with Sadolin Quick Dry Woodstain . Do not use Sadolin Quick Dry Woodstain on substrates which have had water-repellent preservative treatments applied. Where possible, the first coat should be applied all round prior to fixing.
Base Stained Joinery	Lightly abrade, in the direction of the grain. Do not break through the surface coating. Remove all dust. Note: Where there is localised damage, or deterioration has occurred as a result of exposure of the factory coating for longer than 3 months, affected areas should be thoroughly sanded back to a sound substrate and recoated. If a coloured base stain is required in order to match the existing factory applied coating, use Sadolin Quick Dry Woodstain in the most appropriate colour before proceeding as described above. To ensure optimum durability and uniformity of appearance, we recommend finishing with 2 full coats of Sadolin Quick Dry Woodstain .

Glazing	
	The backs of new glazing beads, end grains and rebates should be brought to a finish with Sadolin Quick Dry Woodstain prior to fixing. Joinery to be coated with Sadolin Woodstain systems should be glazed using a suitable sealant. The use of linseed oil putty or modified, non-setting compounds are not recommended in conjunction with our wood protection systems. To confirm compatibility, please consult the manufacturer of the relevant glazing material. Silicone glazing materials should only be applied upon completion of the finishing coats.
Application	
Conditions	Do not apply if there is a risk of rain, or when air / substrate temperatures are below 8°C or above 25°C, or the relative humidity is above 80% during application or drying periods. Protect from frost and rain until dry. Failure to meet these requirements may adversely affect the drying, visual quality and durability of the finish.
Initial Procedure	Ensure product is thoroughly stirred before and during application, otherwise sheen and colour variations may be experienced. Sadolin Quick Dry Woodstain is supplied ready for use. Do not thin.
Applying the Product	Sadolin Quick Dry Woodstain should be applied in a full flowing coat ensuring all surfaces and end grains are fully coated. For best results use a good quality brush specifically designed for use for the application of water borne products. Pay special attention to end grain, tops and bottoms of doors, and undersides of cills. Following surface preparation in accordance with the manufacturers recommendations, finish with 2 full coats of Sadolin Quick Dry Woodstain allowing a minimum of 4 hours drying between coats.
Maintenance	The need for maintenance is indicated by a lightening in colour, reduction in sheen as the coating erodes, and a loss of water repellence. All defective coatings should be completely removed. Any grey denatured exposed timber surfaces must be thoroughly sanded back to clean, bright timber. Organic growths must be removed and infected surfaces should be treated with a suitable fungicidal solution. Remaining sound surfaces should be cleaned using a warm water and mild detergent and rinsed thoroughly with clean water. Bare timber should be patch primed with one or more coats of Sadolin Quick Dry Woodstain in the appropriate colour to match existing colour. Finish with 1 or 2 coats of Sadolin Quick Dry Woodstain as required.
Cleaning Equipment	Clean brushes and equipment with warm, soapy water and rinse with clean water immediately after use. If spilled, Sadolin Quick Dry Woodstain should be removed immediately while still wet, using clean water.
Storage	Ensure this pack is stored upright and secure at all times. Crown Paints Limited cannot accept liability for damage caused by spillage. Do not store below 5°C or above 40°C.
Relevant Standards	BS 6150: 2006 - Code of practice for painting of buildings. BS 8000: Part 12 : 1989 - Workmanship on building sites. Code of practice for decorative wallcoverings and painting. BS EN 927-1 : 1997 - Coating materials and coating systems for exterior wood Part 1: Classification and selection. BS 6262: 1982 Glazing for buildings. BS 8000-7: 1990 - Workmanship on Building Sites. Code of practice for glazing. BS EN 335-2: 1992 - Durability of wood and wood based products - Definition of hazard classes of biological attack. Part 2: Application to solid wood. BS EN 350-2: 1994 - Durability of wood and wood-based products - Natural durability of solid wood. Information on British Standards can be obtained from the British Standards Institute, tel: 0208 996 9001.
Health, Safety and the Environment	
	<p>It is the policy of Crown Paints to provide the highest standard of safety, health and environmental advice and information. To this end, material safety data sheets covering every product are supplied to our customers and are freely available to users on request, by contacting us on the number given below. The safety phrases on the containers and material safety data sheets should be read before using this product.</p> <p>Removal of lead paint. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. Remove all such coating materials in accordance with the appropriate legislation. A guide on "How to remove old lead paint safely" is available via the British Coatings Federation Ltd. (Tel. 01372 360660).</p> <p>Surface Preparation and Applications. Treatments such as sanding and burning off, etc. of paint films may generate hazardous dust and/or fumes. Work in well ventilated areas. Use suitable personal respiratory equipment together with any other Personal Protection Equipment (PPE) as necessary.</p> <p>Environment --- Crown Paints are committed to achieving the highest standards of health and safety at work and to minimising any impact our operations and products may have on the quality of the environment. We will provide such information as is necessary to customers to ensure so far as is reasonably practicable that our products can be used, transported, stored and disposed of safely without risk to health or the environment.</p> <p>It is recommended that any waste material be taken to a household waste disposal site provided by your Local Authority. Do not empty waste materials into drains, watercourses or access routes to septic tanks.</p> <p>Customer Service details For help or more information contact our Customer Relations Team on 0844 7708 998. Before using this product please ensure you have the latest information.</p> <p>The above information is correct at the date of issue, August 2014.</p>