



WOOD FINISHES DIRECT

The following Technical Datasheet is provided by **Sandtex Trade**

Wood Finishes Direct cannot be held liable for the information contained within this document.

For purchasing information visit:
[Sandtex Trade 365 All Weather Masonry Paint](#)

365 ALL WEATHER SMOOTH MASONRY PAINT

A solvent based, premium quality, smooth matt protective and decorative finish. For use on most exterior masonry surfaces and exterior grade building boards. The coating has the unique ability to dry in adverse weather conditions and temperatures as low as -10°C. This product offers up to 20 Years Protection.

AVAILABILITY	
Colour range	Refer to current Sandtex Trade literature
Packaging	5L
PROPERTIES	
Suitable Surfaces	Concrete, render, stone, brick, block and most exterior grade building boards
Drying time @ 20°C/65%RH	Resistant to showers after 20 minutes Touch dry: 1-2 hours. Recoat: 16 hours. Colder/hotter substrates and temperature conditions will affect drying times
Finish	Flat Matt
Composition	Pigment: Titanium Dioxide, light fast coloured pigments and extenders. Resin: Plasticised Pliolite® Solvent: Dearomitted White Spirit Blend
Spreading rate	Up to 10m ² per litre on smooth surfaces. On textured surfaces the spreading rate will be reduced
Wet film thickness	100 micrometres at 10m ² per litre
Dry film thickness	44 micrometres at 10m ² per litre
Volume solids	44% Brilliant White other colours will vary
Flash point	40°C (closed cup)
VOC content	EU limit value for this product (cat.A/c): 430 g/l (2010) This product contains max. 429 g/l VOC.
Limitations	Do not apply if there is a risk of heavy rain. Do not use on bitumen coatings. The decoration of Fletton brickwork either facings or commons is not recommended.
PREPARATION	
New Surfaces	All surfaces must be sound, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Fill cracks and small defects in masonry surfaces with Sandtex Ready Mixed Filler and finish to match existing. Surfaces with excessive suction, chalky residues or loose particles should be treated with Sandtex Trade Stabilising Solution .



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG. Tel: 01254 704951

Crown Paints Ireland Ltd, Unit 8A, Coolmine Central, Porters Road, Coolmine Ind Est, Dublin 15, D15 AX9A. Tel: 00353 1 8164400

TECHNICAL DATA SHEET

<p>Aged Undecorated or Previously decorated surfaces</p>	<p>All surfaces must be sound, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Remove all loose, and failing or suspect material by scraping or brushing with a stiff bristle brush (not wire) to a sound edge. Organic growth must be treated with Sandtex Fungicidal Wash and removed. For surfaces in poor condition mechanical means may be necessary e.g. pressure washing between 1500-2000 psi (102-136 bar), proprietary paint removal system, wet or dry grit blasting. Care must be taken not to damage the underlying surface. Fill cracks and small defects in masonry surfaces with Sandtex Ready Mixed Filler. Stabilise all bare, filled and previously decorated chalking areas with an application of Sandtex Trade Stabilising Solution. Wash any soundly adhering gloss painted surfaces with hot water and liquid detergent solution to remove any contaminants frequently changing the water. Wet abrade to provide a key. Rinse thoroughly with clean water to remove all residues. Allow to dry.</p>
<p>COATING SYSTEM</p>	<p>Apply two full coats. Certain colours may require additional coats to give complete obliteration.</p>
<p>APPLICATION</p>	<p>Stir well before use. Apply using good quality tools, by synthetic brush, medium or long pile roller depending on surface texture, or by airless spray.</p> <p>For airless spray use a minimum fluid pressure of 2000psi (136 bar) and a minimum tip size of 0.018 thou. Mask as necessary with a wet strength grade masking paper. For further information follow the spray manufacturer's guidelines.</p> <p>Ensure the previous coat is fully dry before further application.</p> <p>Always intermix (box) packs for colour consistency. Please check for colour accuracy prior to application. Crown Paints is not liable for decorating costs caused as a result of an incorrect colour being applied.</p>
<p>CLEANING</p>	<p>Return surplus material to container. Clean tools & equipment with a proprietary cleaner immediately after use.</p>
<p>STORAGE</p>	<p>Store upright and secure. Store in secure dry conditions inaccessible to children or animals. Containers should be kept closed during storage. Do not store below 5°C or above 40°C.</p>
<p>MAINTENANCE INFORMATION</p>	<p>Between maintenance redecoration surfaces may be washed with a warm water and liquid detergent solution to remove surface dirt.</p>
<p>HEALTH AND SAFETY</p>	<p>Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Customer Relations Team. When preparing the surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Sandtex Trade products are freely available from the place of purchase or the address below. Do not empty into drains, watercourses or access routes to septic tanks.</p>
<p>GENERAL INFORMATION</p>	<p>Apply all products in accordance with BS 6150: Code of practice for painting of buildings and BS 8000: Part 12: Code of practice for decorative wallcoverings and painting.</p> <p>Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Final results cannot be guaranteed by Crown Paints as it has no control over the conditions under which its products are applied.</p> <p>Before using this product, please ensure you have the latest information. For help or more information contact the Sandtex Trade Customer Relations Team on:</p> <p>Tel: 0330 0240 302.</p> <p>e-mail: info@sandtextrade.co.uk</p> <p>website: www.sandtextrade.co.uk</p> <p>This information is correct at date of issue March 2023.</p>



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG. Tel: 01254 704951

Crown Paints Ireland Ltd, Unit 8A, Coolmine Central, Porters Road, Coolmine Ind Est, Dublin 15, D15 AX9A. Tel: 00353 1 8164400